# KENDEX®

## INDUSTRIAL PRODUCTS

# KENDEX® 0750

**(C.A.S. 64741-88-4)**

| | |
|---|---|
| **Category:** | BASE OIL (GROUP 1) |
| **Generic Name:** | FINISHED 750 SUS NEUTRAL |
| **Description:** | HEAVY VISCOSITY BASE OIL |
| **Product Code:** | R10-4309 |
| **Applications:** | LUBRICANT FORMULATIONS |

| ASTM METHOD | DESCRIPTION | TYPICAL | SPECIFICATION | | |
|---|---|---|---|---|---|
| | | VALUE | MIN | | MAX |
| | LB/GAL | 7.39 | | | |
| D-4052 | GRAVITY, API | 28.0 | 27.0 | | 29.0 |
| D-445 | VISCOSITY @ 40ºC, cSt | 163 | | | |
| D-445 | VISCOSITY @ 100ºC, cSt | 14.0 | 13.00 | | 17.00 |
| D-2270 | VISCOSITY INDEX | 92.0 | 90.0 | | |
| D-92 | FLASH POINT, ºF (COC) | 540 | 475 | | |
| D-5949 | POUR POINT, ºC | -15 | | | -12 |
| D-1500 | COLOR, ASTM | OPAQUE | | | |
| D-6304 | KARL FISHER MOISTURE, PPM | | | | 100 |
| D-2622 | SULFUR, WT% | 0.12 | | | |
| D-2007 | CLAY GEL ANALYSIS, WT% | | | | |
| | SATURATES | 75.5 | | | |
| | POLAR COMPOUNDS | 2.7 | | | |
| | AROMATICS | 21.8 | | | |

**Rev. 4/27/10**

*THE CHEMICAL, PHYSICAL, AND PHYSIOLOGICAL PROPERTIES OF THIS PRODUCT HAVE NOT BEEN FULLY INVESTIGATED AND ITS HANDLING, MIXING WITH INCOMPATIBLE CHEMICALS OR USE MAY BE HAZARDOUS. THIS PRODUCT IS FOR INDUSTRIAL USE ONLY. DO NOT INGEST. KEEP AWAY FROM CHILDREN. MATERIAL SAFETY DATA SHEETS ARE AVAILABLE UPON REQUEST.*

*NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING PATENT WARRANTIES, OR WARRANTIES OF MERCHANTABILITY OF FITNESS FOR USE, ARE MADE BY AMERICAN REFINING GROUP, INCORPORATED WITH RESPECT TO PRODUCTS DESCRIBED OR INFORMATION SET FORTH HEREIN, NOTHING CONTAINED HEREIN SHALL CONSTITUTE A PERMISSION OR RECOMMENDATION TO PRACTICE ANY INVENTION COVERED BY A PATENT WITHOUT A LICENSE FROM THE OWNER OF THE PATENT.*

AMERICAN REFINING GROUP, INC.

ARB102 (5/02)

77 North Kendall Avenue • Bradford, Pennsylvania • 16701 • Phone: 814.368.1200
Fax 814.368.4563 • e-mail:arg@amref.com • www.amref.com • ISO 9001:2008