

WAXES & PETROLATUM SUMMARY

TYPICAL SPECIFICATIONS					
TEST METHODS	ASTM METHOD	Kendex® Light Neutral Slack Wax	Kendex® Medium Neutral Slack Wax	Kendex® Heavy Neutral Slack Wax	Kendex® 0111 Petrolatum
Gravity, API	D1298	44.7	40.9	32.0	31.5
Pounds/gallon		6.70	6.85	7.22	7.24
Melting Point °F (°C)	D87	100 (37.8)	120 (48.9)	139 (59.4)	-----
Drop Melting Point °F (°C)	D127	-----	-----	-----	147 (63.9)
Kinematic Viscosity, cSt @ 100 °C	D445	2.3	3.7	9.5	20.0
Viscosity @ 210 °F, SUS	D2161	33.8	38.5	57.5	98.5
Oil Content, Wt%	D721	6.0	6.0	16	10
Flash Point (C.O.C.), °F (°C)	D92	365 (185)	430 (221)	525 (274)	590 (310)
ASTM Color	D1500	L0.5	L1.0	8.0	8.0
Cone Penetration @ 77 °F (25 °C), dmm	D937	-----	-----	-----	90

THE CHEMICAL, PHYSICAL, AND PHYSIOLOGICAL PROPERTIES OF THIS PRODUCT HAVE NOT BEEN FULLY INVESTIGATED AND ITS HANDLING, MIXING WITH INCOMPATIBLE CHEMICALS, OR USE MAY BE HAZARDOUS. THIS PRODUCT IS FOR INDUSTRIAL USE ONLY. DO NOT INGEST. KEEP AWAY FROM CHILDREN. MATERIAL SAFETY DATA SHEETS ARE AVAILABLE ON REQUEST.

NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING PATENT WARRANTIES, OR WARRANTIES OF MERCHANTABILITY OF FITNESS FOR USE, ARE MADE BY AMERICAN REFINING GROUP, INCORPORATED WITH RESPECT TO PRODUCTS DESCRIBED OR INFORMATION SET FORTH HEREIN. NOTHING CONTAINED HEREIN SHALL CONSTITUTE A PERMISSION OR RECOMMENDATION TO PRACTICE ANY INVENTION COVERED BY A PATENT WITHOUT A LICENSE FROM THE OWNER OF THE PATENT.



AMERICAN REFINING GROUP, INC.

77 North Kendall Ave. • Bradford, PA • 16701 • Phone 814.368.1200
Fax 814.368.4563 • e-mail: arg@amref.com • www.amref.com