



KENWAX®

WAXES & PETROLATUM SUMMARY

TYPICAL PROPERTIES					
	ASTM METHOD	Kenwax® Light Neutral Slack Wax	Kenwax® Medium Neutral Slack Wax	Kenwax® Heavy Neutral Slack Wax	Kenwax® 0111 Petrolatum
Gravity, API	D1298	44.7	40.9	32.0	31.5
Pounds/gallon		6.70	6.85	7.22	7.24
Melting Point °F	D87	100 (37.8)	120 (48.9)	139 (59.4)	-----
Drop Melting Point	D127	-----	-----	-----	147 (63.9)
Kinematic	D445	2.3	3.7	9.5	20.0
Viscosity @ 210 °F.	D2161	33.8	38.5	57.5	98.5
Oil Content, Wt%	D721	6.0	6.0	16	10
Flash Point	D92	365 (185)	430 (221)	525 (274)	590 (310)
ASTM Color	D1500	L0.5	L1.0	8.0	8.0
Cone Penetration	D937	-----	-----	-----	90



Specialty Refining Solutions®

www.amref.com

814-368-1200

