

Kendex® HNE

PROD. CODE
4579

Heavy neutral extract designed for use in the rubber and asphalt industry via solvent extraction.

FEATURES & BENEFITS

- High aromatic content
- Improved compatibility with Natural Rubber (NR), Styrene-Butadiene Rubber (SBR), and Polybutadiene Rubber (PBR)
- Cost effective solution

APPLICATIONS

Rubber process oil for custom mixing and general rubber goods; Asphalt modifier and rejuvenator; Polymer Modified Asphalt (PMA) paving and roofing; Plasticizer for adhesives and coatings

METHOD	DESCRIPTION	TYPICAL
	LBS/GAL	8.31
D4052	API GRAVITY	10.5
D4052	SPECIFIC GRAVITY	0.997
D2501	VISCOSITY GRAVITY CONSTANT	0.932
D445	VISCOSITY @ 40°C, cSt	7,100
D445	VISCOSITY @ 100°C, cSt	82
D2161	VISCOSITY @ 100°F, SUS	42,437
D2161	VISCOSITY @ 210°F, SUS	404
D2270	VISCOSITY INDEX	-11
D5949	POUR POINT, °C (°F)	39 (102)
D92	FLASH POINT, COC, °C (°F)	271 (520)
D1500	COLOR	D8.0
D2007	SATURATES, wt %	25.5
D2007	AROMATICS, wt %	51.2
D1218	REFRACTIVE INDEX @ 20°C	1.56665
D611	ANILINE POINT, °C	65.2
D4294	SULFUR, ppm	3,750
D4530	CARBON RESIDUE, MICRO METHOD wt %	6.1

Mixing with incompatible chemicals may be hazardous. This product is for industrial use only. Safety data sheets are available upon request. No warranties expressed or implied, including patent warranties or warranties of merchantability or fitness for a particular purpose, are made by American Refining Group, Inc., with respect to products described or information set forth herein. Nothing contained herein shall constitute a permission or recommendation to practice any invention covered by a patent without a license from the owner of the patent.



amref.com | 814.368.1200

**AMERICAN
REFINING
GROUP, INC.**
Refine everything.™