

FEATURES & BENEFITS

- Improved quality for hard virgin asphalts
- Improved processability
- Increased durability

APPLICATIONS

Low temperature modifier for asphalt; Viscosity reducer for Polymer Modified Asphalt (PMA); Recycled asphalt and shingle rejuvenator; Rubber process oil for custom mixing and general rubber goods

METHOD	DESCRIPTION	TYPICAL
	LBS/GAL	7.74
D4052	API GRAVITY	21.1
D4052	SPECIFIC GRAVITY	0.927
D2501	VISCOSITY GRAVITY CONSTANT	0.881
D445	VISCOSITY @ 40°C, cSt	50.2
D445	VISCOSITY @ 100°C, cSt	6.7
D2161	VISCOSITY @ 100°F, SUS	260
D2161	VISCOSITY @ 210°F, SUS	49
D2270	VISCOSITY INDEX	81
D5949	POUR POINT, °C (°F)	-30 (-22)
D92	FLASH POINT, COC, °C (°F)	216 (420)
D1500	COLOR	D8.0
D2007	SATURATES, wt %	45.3
D2007	AROMATICS, wt %	50.8
D1218	REFRACTIVE INDEX @ 20°C	1.51545
D611	ANILINE POINT, °C	70.8
D4294	SULFUR, ppm	2,329
D4530	CARBON RESIDUE, MICRO METHOD wt %	0.3

Mixing with incompatible chemicals may be hazardous. This product is for industrial use only. Safety data sheets are available upon request. No warranties expressed or implied, including patent warranties or warranties of merchantability or fitness for a particular purpose, are made by American Refining Group, Inc., with respect to products described or information set forth herein. Nothing contained herein shall constitute a permission or recommendation to practice any invention covered by a patent without a license from the owner of the patent.

